



Er referens:

Vår referens: Morgan Larsson

Datum: 2021-03-02

CHEMICAL RESISTANCE TABLE**Immersion Testing**

Synko-Flex FR will have the following typical results when exposed to the following medias when submerged:

MATERIAL	SOLUTION CONCENTRATION	RESULTS
Gasoline	100%	Slight Swell
Jet A Fuel	100%	Slight Swell
JP-4 Fuel	100%	Slight Swell
Kerosene	100%	Slight Swell
Motor Oil	100%	No Effect
Transmission Fluid	100%	Slight Swell
Brake Fluid	100%	Very slight Swell
Cooking Oil	100%	No Degradation
Mineral Spirits	100%	No Degradation
Methyl Ethyl Ketone	100%	Excess Swelling
Toluene	100%	25% Swelling
Tri Chlorethane	100%	Excess Softening
Alcohol	100%	No Effect
Anti Freeze	100%	No Effect
Runway De-Icers	100%	No Effect
Cleaning Detergents	100%	No Effect
Insecticides	100%	No Effect
Fertilizers	100%	No Effect