



Er referens:

Vår referens:

Datum: Mars 2023

## TEKNISKT DATABLAD

### Plastfolie Åldersbeständig 0.2 mm

#### TECHNICAL DATA

<b>Material:</b>	PELD			
<b>Material additives:</b>	Stabilized for long time duration			
<b>Colour:</b>	Transparent			
<b>Special properties:</b>	Full fills the Swedish P-mark and CE-declaration			
<b><i>Parameter:</i></b>	<b><i>Value:</i></b>	<b><i>Unit:</i></b>	<b><i>Tol.±:</i></b>	<b><i>Method:</i></b>
<b>Width:</b>	2700	mm	5	
<b>Thickness (nom.):</b>	200	my	5%	SS241013
<b>Reel length:</b>	25	m	-	
<b>Core inside Ø:</b>	38	mm		
<b>Gross weight approx.:</b>	12,5	kg		
<b>Pallet weight approx.:</b>	625	kg		
<b>Reels per pallet:</b>	50			
<b>Dartdrop:</b>	300	g		ASTM D1709
<b>Tear Strenght MD:</b>	4000	mN		ISO 6383-2
<b>Tear Strenght TD:</b>	8000	mN		ISO 6383-2
<b>Tensile Stress MD:</b>	22	MPa		ISO 527-3
<b>Elongation at break MD:</b>	550	%		ISO 527-3
<b>Fuktbeständighet:</b>	3* 10E6	s/m		EN 1931

#### ADDITIONAL INFORMATION

<b>Man. system:</b>	The organisation holds certificates for ISO 9001 and ISO 14001
<b>Hygiene:</b>	Following Reach 1907/2006/CE
<b>Safety:</b>	Safety datasheets and certifications available upon request
<b>Waste handling:</b>	All packaging components are suitable for reuse, material recycling or energy recovery

This information is only meant as guidance to simplify the choice and use of products, but cannot guarantee its suitability in specific cases.

